Top- and clear coat sanding process





Mirka® DEROS II 650CV 150 mm, orbit 5 mm

Mirka® PS1437 Polisher, 150 mm

Defect removal STEP Net interface + Galaxy 150mm,

Grit 1200-1500



STEP 3

STEP 1



Abralon J3 150mm, Grit 3000



Polarshine® Marine Medium Cut Compound + Lambswool pad Pro



STEP 2 (Dark)





SANDING



STEP 1

• Start sanding with Mirka® DEROS II 650CV using a Net Interface and Galaxy 1200 or 1500 grit.



STEP 2

- Clean the surface between every sanding step to avoid contamination and get a better visibility of the sanding progress.
- Continue sanding with Galaxy 2000 grit





STEP 3

• Continue wet sanding with Abralon® J3 3000.

POLISHING



STEP 1

• Polish the surface with **Polarshine**® **Marine Medium Cut Compound** and a Lambswool pad PRO together with Mirka® PS1437 Polisher to eliminate sanding scratches.



STEP 2 (Light colours)

• For light coloured surfaces, change to Polarshine® Marine Fine Compound, Antihologram with a Yellow Waffle polishing foam pad. Wipe off excess polishing compound.



STEP 2 (Dark colours)

• For dark coloured surfaces, continue with Polarshine® 12 Black with a Black Waffle M foam pad to remove any polishing marks, haze and holograms. Wipe off excess compound.

NOTE! By extending the sanding process and using finer grits, the polishing time will shorten and lower the total production time and cost.