



Action: Sand the table and resin.
Use: Galaxy 120, followed by 180.




Action: Sand the resin.
Use: Galaxy 320, followed by 600, then 1000 and 1500.



Action: Sand the resin.
Use: Abralon® J3 77mm, damp, 2000 followed by 3000.



Action: Polish the resin.
Use: Polarshine® 10 and yellow waffle pad.



Action: Apply a coating to the whole surface to finish.

